

ULR - TC61762000014800P

TEST REPORT

Report No. : CH:TX:1142015131

DATE : 28/05/2020



SRF LIMITED

PLOT NO.K-1,SIPCOT INDUSTRIAL COMPLEX, GUMMIDIPOONDI
Tamil Nadu, Thiruvallur-601201

IN


CONTACT PERSON : ANGELINE DIVYA

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION	COATED FABRIC PU COATED FABRIC FOR MEDICAL PPE
COLOUR	WHITE (AS IDENTIFIED BY THE LABORATORY)
COUNTRY OF DESTINATION	INDIA
COUNTRY OF ORIGIN	INDIA
SAMPLE RECD ON	25/05/2020 TESTING PERIOD : 25/05/2020 - 28/05/2020

Summary of Test Results		
Test Method	Test Name	Status / Performance Level
ASTM F1670/F 1670 M - 08 (2017)	Determination of resistance of protective clothing material	
	Synthetic Blood penetration test	Pass

Per pro SGS India Private Ltd.



KARTHIKEYAN.K
TECHNICAL MANAGER

Email your Test Report Related Enquiries at Feedback.SLT@sgs.com



TEST REPORT

Report No. : CH:TX:1142014957

DATE : 02/06/2020



SRF LIMITED

PLOT NO.K-1, SIPCOT INDUSTRIAL COMPLEX, GUMMIDIPOONDI
Tamil Nadu, Thiruvallur-601201
IN

CONTACT PERSON : ANGELINE DIVYA

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

PRODUCT DESCRIPTION COATED FABRIC
PU COATED FABRIC FOR MEDICAL PPE
COLOUR WHITE (AS IDENTIFIED BY THE LABORATORY)
COUNTRY OF DESTINATION INDIA
COUNTRY OF ORIGIN INDIA
SAMPLE RECD ON 21-May-2020 **TESTING PERIOD :** 21/05/2020 - 02/06/2020

RESULT SUMMARY

TESTS	PASS	FAIL	REMARKS
AIR PERMEABILITY OF TEXTILE FABRICS			REFER RESULTS

per pro SGS India Private Ltd.

R E S U L T S

REQ

AIR PERMEABILITY OF TEXTILE FABRICS

ISO 9237:1995

Machine Type: Textest FX3300 Air Permeability Tester III

Test Condition: Test side (Coated side)

Test Pressure: 100 Pa

Test Area: 20 sq.cm

Individual reading (Unit:mm/s):

- (1): 0
- (2): 0
- (3): 0
- (4): 0
- (5): 0
- (6): 0
- (7): 0
- (8): 0
- (9): 0
- (10): 0

Average: 0

S.D: 0

Minimum: 0

Maximum: 0

CV%: 0

S. NAGENDRA KUMAR

EXECUTIVE

Email your Test Report Related Enquiries at Feedback.SLT@sgs.com

TEST REPORT

Report No. : CH:TX:1142015132

DATE : 28/05/2020



SRF LIMITED

PLOT NO.K-1, SIPCOT INDUSTRIAL COMPLEX, GUMMIDIPOONDI
Thiruvallur-601201
IN

CONTACT PERSON : ANGELINE DIVYA

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION	WOVEN FABRIC PU COATED FABRIC FOR MEDICAL PPE WHITE (AS IDENTIFIED BY THE LABORATORY)
COLOUR	WHITE (AS IDENTIFIED BY THE LABORATORY)
QTY SUBMITTED	1.40M X 3 M - 1NO
COUNTRY OF DESTINATION	INDIA
COUNTRY OF ORIGIN	INDIA
SAMPLE RECD ON	25/05/2020

TESTING PERIOD : 25/05/2020 - 28/05/2020

RESULT SUMMARY

TESTS	PASS	FAIL	REMARKS
WATER REPELLENCY			REFER RESULTS

WATER REPELLENCY

IS 390:1975

RATING 100

INTERPRETATION:

- 100: No Sticking or wetting of upper surface.
- 90: Slight random sticking or wetting of upper surface.
- 80: Wetting of upper surface at spray point.
- 70: Partial wetting of whole of upper surface.
- 50: Complete wetting of whole of upper surface.
- 0: Complete wetting of whole of upper and lower surface.

Note: Test is performed on Non-coated side only as per customer request.

SAMPLE IMAGE



per pro SGS India Private Ltd.

G. NAGESWARA RAO
EXECUTIVE

Email your Test Report Related Enquiries at Feedback.SLT@sgs.com

ULR - TC61762000015043F

TEST REPORT

Report No. : CH:TX:1142015133

DATE : 28/05/2020



SRF LIMITED

PLOT NO.K-1, SIPCOT INDUSTRIAL COMPLEX, GUMMIDIPOONDI
Tamil Nadu, Thiruvallur-601201
IN

CONTACT PERSON : ANGELINE DIVYA

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

PRODUCT DESCRIPTION	WOVEN FABRIC	
	PU COATED FABRIC FOR MEDICAL PPE	
COLOUR	WHITE (AS IDENTIFIED BY THE LABORATORY)	
QTY SUBMITTED	1.40M X 3 M - 1NO	
COUNTRY OF DESTINATION	INDIA	
COUNTRY OF ORIGIN	INDIA	
SAMPLE RECD ON	25-May-2020	TESTING PERIOD : 25/05/2020 - 28/05/2020

RESULT SUMMARY

TESTS	PASS	FAIL	REMARKS
HYDROSTATIC TEST			REFER RESULTS

per pro SGS India Private Ltd.

G. NAGESWARA RAO
EXECUTIVE

Email your Test Report Related Enquiries at Feedback.SLT@sgs.com

RESULTS

REQ

HYDROSTATIC TEST

AATCC 127:2017- Option 2

Machine Type: Hydrostatic Head Tester
Rate of increase of water pressure: 60mbar/min
Test Condition: 20 Dec, RH 65%
Test Side: Face side (Coated side)
Distilled Water Temperature: 20°C
Result:

Water Column (mbar):

- Specimen 1: 361#
- Specimen 2: 350#
- Specimen 3: 349#
- Average: 353.3#

#: Water droplets are observed.

Note: Test is performed as per Customer's request.

***** End of Page*****